FABRIC SOFT 20	FABRIC SOFT 07	FABRIC SOFT 17	FABRIC SOFT 26	FABRIC SOFT 22
FABRIC SOFT 06	FABRIC SOFT 08	FABRIC SOFT 23	FABRIC SOFT 03	FABRIC SOFT 29
FABRIC SOFT 19	FABRIC SOFT 39	FABRIC SOFT 44	FABRIC SOFT 24	FABRIC SOFT 14
FABRIC SOFT 38	FABRIC SOFT 12	FABRIC SOFT 31	FABRIC SOFT 09	FABRIC SOFT 18
FABRIC SOFT 16	FABRIC SOFT 34			

Fabric Soft

Width: 140 cm • Weight: 920 g/ml

Colour fastness to light = 5^{***} - EN ISO 105-B02

Colour fastness to rubbing wet = $3-4^{***}$ - EN ISO 105-X12

Colour fastness to rubbing dry = $4-5^{****}$ - EN ISO 105-X12

Pilling: 4-5**** - ISO 12945-2 • Composition: 45% viscose, 35% cotton, 20% polyester

Abrasion: 27.000 *** - EN ISO 12947-2 • Cleaning instruction: $\Join lpha \supseteq \textcircled{P} oxed{M}$ • Edge: \leftrightarrow

Classification for upholstery to be used in privat home: * poor ** caution *** acceptable **** good ***** very good

The fabric changes appearance depending on the angle from which it is viewed. The change can range from a more matt and darker surface to a shinier and lighter coloured one. The change is also noticeable in those areas where the fabric is exposed to wear and tear. This change is typical of velour fabrics and is an expected and intrinsic feature of this material.

